



KOB AU Glasgitter-Gewebe E 26 / 23



Type of crack



Field of application / properties

KOB AU Glasgitter-Gewebe E 26 / 23 is intended for the reinforcement of mineral plasters according to DIN 18550 and polymer modified adhesives and reinforcing mortars in case of cracks passing through the plaster layers type A.2 according to the classification in the BFS notice no. 19. KOB AU Glasgitter-Gewebe E 26 / 23 is of the non-slip type, non-swelling, resistant to alkalis and chemicals as well as non-fouling.

For use inside and outside.

Processing

Prepare the surface to be reinforced according to the national regulations and/or BFS notices. Subsequently, apply embedding material, e.g. plaster according to DIN 18550 and/or the instructions of the manufacturer. Embed KOB AU Glasgitter-Gewebe E 26 / 23 from the roll or as a ready-cut in the wet coating avoiding wrinkle formation and bubbles. The webs should overlap in a width of at least 10 cm. Subsequently, apply another coat of embedding material uniformly so that the fabric is no longer visible.

Further work is to be performed observing the instructions of the manufacturer in each case.

Technical data

Quality	Textile glass fibre
Colour	natural white
Stabilization	SBR
Spec. weight DIN 53854	abt. 165 g / m ²
Thickness	abt. 500 µm
Mesh width	abt. 4 x 4 mm
Max. longitudinal tensile force	abt. 1750 N / 5 cm
Max. transverse tensile force	abt. 1750 N / 5 cm
Longitudinal elongation	abt. 4 %
Transverse elongation	abt. 4 %

Delivery form

Roll dimensions: 1.00 m x 50 m
(other dimensions on request)

Tools / embedding material

- Smoothing tool, leveler
- Embedding material according to the manufacturer

Storage

dry, cool, in closed spaces

Note

The above statements reflect the current stage of development and make no claim to be exhaustive. As the application and use of our product is beyond our control and variations in use, modes of operation and materials must be tailored to the prevailing working conditions, this technical information cannot be regarded as legally binding. This edition supersedes previous technical instructions.