



KOB AU Glasgitter-Gewebe 5 / 5 A



Type of crack / symbol



Field of application / properties

KOB AU Glasgitter-Gewebe 5 / 5 A is intended for the reinforcement of plasters and fillers in case of plaster surface cracks type A.1 according to the classification in the BFS notice no. 19. When using elastic intermediate coatings, KOB AU Glasgitter-Gewebe 5 / 5 A can also be deployed for the crack type B.1. The technique "Reinforcement instead of multiple leveling" allows smoothening of rough substrates such as fibre glass wallpapers or mottled stone plaster in one operation. The KOB AU Glasgitter-Gewebe 5 / 5 A is of the non-slip type, watertight, resistant to alkalis, chemicals and is non-fouling.

For use inside and outside.

Processing

Plaster reinforcement:

Prepare the surface to be reinforced according to the national regulations and/or BFS notices. Subsequently, apply embedding material according to the instructions of the manufacturer. Embed KOB AU Glasgitter-Gewebe 5 / 5 A from the roll or as a ready-cut in the wet coating avoiding wrinkle formation or bubbles. The webs should overlap in a width of approx. 5-10 cm. Subsequently, apply another coat of embedding material uniformly so that the fabric is no longer visible.

KOB AU technique "Reinforcement instead of multiple leveling":

In order to achieve smooth surfaces, apply a suitable filler mechanically or manually on the substrate and comb uniformly using a toothed trowel of 4x6x4 mm. Insert the KOB AU Glasgitter-Gewebe 5 / 5 A into the fresh filler and level it completely by means of a smoothening tool with toothed trowel structure below the fabric. The webs should overlap at least 5 cm. The embedding material penetrating the grid structure is to be used for covering and including the overlapping area without any transition.

Technical data

Quality	▶ Textile glass fibre
Colour	▶ natural white
Stabilization	▶ SBR
Spec. weight DIN 53854	▶ abt. 60 g / m ²
Mesh width	▶ abt. 1.2 x 1.2 mm
Max. longitudinal tensile force	▶ abt. 800 N / 5 cm
Max. transverse tensile force	▶ abt. 550 N / 5 cm
Longitudinal elongation	▶ abt. 4 %
Transverse elongation	▶ abt. 3 %

Delivery form

Roll dimensions: 1.00 m x 50 m
(other dimensions on request)

Tools

- Filler, knife, smoothening tool
- Toothed trowel 4x6x4 mm

Required material

approx. 2.4 l / m² light dispersion filler

Storage

dry, cool, in closed spaces

Note

Perform subsequent work taking into account the instructions of the manufacturer in each case. Extreme roughness or coarse unevenness are to be eliminated prior to carrying out the KOB AU technique "Reinforcement instead of multiple filling" through scraper filling.

The above statements reflect the current stage of development and make no claim to be exhaustive. As the application and use of our product is beyond our control and variations in use, modes of operation and materials must be tailored to the prevailing working conditions, this technical information cannot be regarded as legally binding. This edition supersedes previous technical instructions.